

DERBY GASKETS LTD.

www.derbygaskets.com

MATERIAL SPECIFICATION

GASKET PAPER

Cellulose fibre impregnated with glue/plasticiser

Temperature: 120C

Compressibility: Load of 1000 lbs per sq in 25% to 40%

Recovery: 35% min

Tensile Strength: 2000 lb per sq in min

Density: 45 lb per cu ft min

Fluid Ageing: 22 hrs at 70F

ASTM Oil No. 3: weight increase 20% max/thickness increase 5% max

ASTM Fuel B: weight increase 20% max/thickness increase 5% max

Water: weight increase 100% max/thickness increase 30% max

Tolerance on thickness: +/- 10%

Specifications: ASTM 3313 B and BS4249

We reserve the right to alter the specification without notice.
Values given may vary according to manufacturing tolerances.

It is the responsibility of the purchaser to ensure material is suitable for purpose and we will provide samples for test if required