

DERBY GASKETS LTD.

www.derbygaskets.com

MATERIAL SPECIFICATION

SILICONE SPONGE

Quality:	Commercial
Density:	16 lbs/cu.ft (Sil 16)
Elongation:	N/A
Compression Set (150°C for 70 hours) Recovery Period 48 hours 25% compression	6% Test Method BS4443 Part 1 Method A
Resistance to Heat Ageing (after 168 hrs @ 150°C) Compression Set (150°C for 70 hrs). Recovery Period 48 hrs 25% compression	5% Test Method BS4443 Part 1 Method A
Operating Temp Range	- 60°C to + 200°C

We reserve the right to alter the specification without notice.

Values given may vary according to manufacturing tolerances.

It is the responsibility of the purchaser to ensure material is suitable for purpose and we will provide samples for test if required